



180002280596



中国认可
国际互认
检测
TESTING
CNAS L0230

检测报告

TEST REPORT

BETC-HJ-2020-D-00458

样品名称: 维护者隔热涂料

委托单位: 维护者新材料(厦门)有限公司

检测类别: 委托检验

国家化学建筑材料测试中心(建工测试部)

CHINA NATIONAL CENTER FOR TEST OF CHEMICAL BUILDING MATERIALS

国家化学建筑材料测试中心（建工测试部）



检测报告

委托编号(Commission No.):2020-003288

报告编号(No. of Report):BETC-HJ-2020-D-00458

第1页 共2页 (Page 1 of 2)

样品名称	维护者隔热涂料	样品编号	HJ-2020-D-00458
委托单位	维护者新材料（厦门）有限公司	规格	-----
		商标	维护者/WELLHOOD
生产单位	维护者新材料（厦门）有限公司	检测类别	委托检验
抽样单位	-----	样品数量	1kg
抽样地点	-----	抽样日期	-----
抽样基数	-----	到样日期	2020-06-02
样品批号	-----	送(抽)样人	刘海生
检测项目	游离甲醛，乙二醇醚及醚酯含量总和，重金属，挥发性有机化合物（VOC）		
检测依据	GB 24408-2009《建筑用外墙涂料中有害物质限量》		
判定依据	GB 24408-2009《建筑用外墙涂料中有害物质限量》		
检测结论	经检测，该样品达到了GB 24408-2009《建筑用外墙涂料中有害物质限量》水性外墙涂料面漆的技术指标要求。 (本页以下无正文)		
仪器	紫外可见分光光度计、气相色谱仪、电感耦合等离子体发射光谱仪		
备注	-----		

批准：

王立君

审核：

张丹

主检：

赵宇航

国家化学建筑材料测试中心（建工测试部）

检 测 报 告

委托编号(Commission No.):2020-003288

报告编号(No. of Report):BETC-HJ-2020-D-00458

第2页 共2页 (Page 2 of 2)

样 品 名 称		维护者隔热涂料		报 告 日 期	2020.6.30
序号	检 测 项 目		技 术 指 标 (水性外墙涂料面漆)	检 测 结 果	单 项 评 定
1	挥发性有机化合物(VOC), g/L		≤150	67.4	合 格
2	乙二醇醚及醚酯含量总和, % (限乙二醇甲醚、乙二醇甲醚醋酸酯、乙二醇乙醚、乙二醇乙醚醋酸酯和二乙二醇丁醚醋酸酯)		≤0.03	未检出	合 格
3	游离甲醛, mg/kg		≤100	11.3	合 格
4	重金属, mg/kg (限色漆和腻子)	铅 (Pb)	≤1000	未检出	合 格
		镉 (Cd)	≤100	未检出	合 格
		六价铬(Cr ⁶⁺)	≤1000	未检出	合 格
		汞 (Hg)	≤1000	未检出	合 格
备 注		1. 游离甲醛的测试方法检出限: 5mg/kg。 2. 乙二醇醚及醚酯测试方法检出限: 0.001%。 3. 挥发性有机化合物(VOC)测试方法检出限: 2g/L。 4. 重金属检出限: 铅: 1.0mg/kg; 镉: 0.1mg/kg; 六价铬: 1mg/kg; 汞: 0.05mg/kg。 5. “未检出”表示检测结果小于检出限。			

注 意 事 项

NOTICE

1. 报告无“检测测试专用章”或检测单位公章无效;

Test report is invalid without the “Stamp of test report” or that of test department on it.

2. 复制报告未重新加盖“检测测试专用章”或检测单位公章无效;

Duplication of test report is invalid without the “Stamp of test report” or that of test department re-stamped on it.

3. 报告无主检、审核、批准签字无效;

Test report is invalid without the signatures of the persons for chief test, verification and approval.

4. 报告涂改无效;

Test report is invalid if altered.

5. 对检测报告若有异议, 应于收到报告之日起十五日内向检测单位提出;

Different opinions about test report should be reported to the test department within 15 days from the date of receiving the test report.

6. 一般情况, 委托检测仅对来样负责, 样品信息由委托方提供。

In general, for entrusted tests the responsibilities are undertaken for the delivered samples only and the sample information is provided by clients.

地 址: 北京市朝阳区北三环东路30号

ADD: NO.30, Beisanhuan East Road, Chaoyang District, Beijing, China

电话(Tel): 010-64517787 010-84281338

投诉电话: 010-64517830

传真(Fax): 010-84288515 010-84281338

邮政编码(Post code): 100013

Internet: <http://www.cabr-betc.com>